

Odporność chemiczna politetrafluoroetylenu (PTFE) na następujące środki według [Cole-Parmer](#)

Chemical	Compatibility
Acetaldehyde	A-Excellent 😊
Acetamide	A-Excellent 😊
Acetate Solvent	A-Excellent 😊
Acetic Acid	A-Excellent 😊
Acetic Acid 20%	A-Excellent 😊
Acetic Acid 80%	A-Excellent 😊
Acetic Acid, Glacial	A-Excellent 😊
Acetic Anhydride	A-Excellent 😊
Acetone	A-Excellent 😊
Acetyl Bromide	A-Excellent 😊
Acetyl Chloride (dry)	A-Excellent 😊
Acetylene	A-Excellent 😊
Acrylonitrile	A-Excellent 😊
Adipic Acid	A-Excellent 😊
Alcohols:Amyl	A-Excellent 😊
Alcohols:Benzył	A-Excellent 😊
Alcohols:Butyl	A-Excellent 😊
Alcohols:Diacetone	A-Excellent 😊
Alcohols:Ethyl	A-Excellent 😊
Alcohols:Hexyl	A-Excellent 😊
Alcohols:Isobutyl	A-Excellent 😊
Alcohols:Isopropyl	A-Excellent 😊
Alcohols:Methyl	A-Excellent 😊
Alcohols:Octyl	N/A
Alcohols:Propyl	A-Excellent 😊
Aluminum Chloride	A-Excellent 😊
Aluminum Chloride 20%	A-Excellent 😊
Aluminum Fluoride	A-Excellent 😊
Aluminum Hydroxide	A-Excellent 😊
Aluminum Nitrate	A-Excellent 😊
Aluminum Potassium Sulfate 10%	A-Excellent 😊
Aluminum Potassium Sulfate 100%	A-Excellent 😊
Aluminum Sulfate	A-Excellent 😊
Alums	A-Excellent 😊

Amines	A-Excellent 😊
Ammonia 10%	A-Excellent 😊
Ammonia Nitrate	A-Excellent 😊
Ammonia, anhydrous	A-Excellent 😊
Ammonia, liquid	A-Excellent 😊
Ammonium Acetate	A-Excellent 😊
Ammonium Bifluoride	A-Excellent 😊
Ammonium Carbonate	A-Excellent 😊
Ammonium Caseinate	N/A
Ammonium Chloride	A-Excellent 😊
Ammonium Hydroxide	A-Excellent 😊
Ammonium Nitrate	A-Excellent 😊
Ammonium Oxalate	N/A
Ammonium Persulfate	A-Excellent 😊
Ammonium Phosphate, Dibasic	A-Excellent 😊
Ammonium Phosphate, Monobasic	A-Excellent 😊
Ammonium Phosphate, Tribasic	A-Excellent 😊
Ammonium Sulfate	A-Excellent 😊
Ammonium Sulfite	A-Excellent 😊
Ammonium Thiosulfate	N/A
Amyl Acetate	A-Excellent 😊
Amyl Alcohol	A-Excellent 😊
Amyl Chloride	A-Excellent 😊
Aniline	A-Excellent 😊
Aniline Hydrochloride	A-Excellent 😊
Antifreeze	N/A
Antimony Trichloride	A-Excellent 😊
Aqua Regia (80% HCl, 20% HNO ₃)	A-Excellent 😊
Arochlor 1248	A-Excellent 😊
Aromatic Hydrocarbons	N/A
Arsenic Acid	A-Excellent 😊
Arsenic Salts	N/A
Asphalt	A-Excellent 😊
Barium Carbonate	A-Excellent 😊
Barium Chloride	A-Excellent 😊
Barium Cyanide	A-Excellent 😊
Barium Hydroxide	A-Excellent 😊
Barium Nitrate	A-Excellent 😊
Barium Sulfate	A-Excellent 😊
Barium Sulfide	A-Excellent 😊

Beer	A-Excellent 😊
Beet Sugar Liquids	A-Excellent 😊
Benzaldehyde	A-Excellent 😊
Benzene	A-Excellent 😊
Benzene Sulfonic Acid	A-Excellent 😊
Benzoic Acid	A-Excellent 😊
Benzol	A-Excellent 😊
Benzonitrile	A-Excellent 😊
Benzyl Chloride	N/A
Bleaching Liquors	A-Excellent 😊
Borax (Sodium Borate)	A-Excellent 😊
Boric Acid	A-Excellent 😊
Brewery Slop	N/A
Bromine	A-Excellent 😊
Butadiene	A-Excellent 😊
Butane	A-Excellent 😊
Butanol (Butyl Alcohol)	A-Excellent 😊
Butter	A-Excellent 😊
Buttermilk	A-Excellent 😊
Butyl Amine	A-Excellent 😊
Butyl Ether	A-Excellent 😊
Butyl Phthalate	A-Excellent 😊
Butylacetate	A-Excellent 😊
Butylene	A-Excellent 😊
Butyric Acid	A-Excellent 😊
Calcium Bisulfate	N/A
Calcium Bisulfide	A-Excellent 😊
Calcium Bisulfite	A-Excellent 😊
Calcium Carbonate	A-Excellent 😊
Calcium Chlorate	A-Excellent 😊
Calcium Chloride	A-Excellent 😊
Calcium Hydroxide	A-Excellent 😊
Calcium Hypochlorite	A-Excellent 😊
Calcium Nitrate	A-Excellent 😊
Calcium Oxide	A-Excellent 😊
Calcium Sulfate	A-Excellent 😊
Calgon	N/A
Cane Juice	A-Excellent 😊
Carbolic Acid (Phenol)	A-Excellent 😊
Carbon Bisulfide	N/A

Carbon Dioxide (dry)	A-Excellent 😊
Carbon Dioxide (wet)	A-Excellent 😊
Carbon Disulfide	A-Excellent 😊
Carbon Monoxide	A-Excellent 😊
Carbon Tetrachloride	A-Excellent 😊
Carbon Tetrachloride (dry)	A-Excellent 😊
Carbon Tetrachloride (wet)	A-Excellent 😊
Carbonated Water	N/A
Carbonic Acid	A-Excellent 😊
Catsup	N/A
Chloric Acid	A-Excellent 😊
Chlorinated Glue	N/A
Chlorine (dry)	A-Excellent 😊
Chlorine Water	A-Excellent 😊
Chlorine, Anhydrous Liquid	A-Excellent 😊
Chloroacetic Acid	A-Excellent 😊
Chlorobenzene (Mono)	B-Good 😊
Chlorobromomethane	A-Excellent 😊
Chloroform	A-Excellent 😊
Chlorosulfonic Acid	A-Excellent 😊
Chocolate Syrup	A-Excellent 😊
Chromic Acid 10%	A-Excellent 😊
Chromic Acid 30%	A-Excellent 😊
Chromic Acid 5%	A-Excellent 😊
Chromic Acid 50%	A-Excellent 😊
Chromium Salts	N/A
Cider	N/A
Citric Acid	A-Excellent 😊
Citric Oils	N/A
Cloroxr (Bleach)	A-Excellent 😊
Coffee	N/A
Copper Chloride	A-Excellent 😊
Copper Cyanide	A-Excellent 😊
Copper Fluoborate	N/A
Copper Nitrate	A-Excellent 😊
Copper Sulfate >5%	A-Excellent 😊
Copper Sulfate 5%	A-Excellent 😊
Cream	A-Excellent 😊
Cresols	N/A
Cresylic Acid	A-Excellent 😊
Cupric Acid	A-Excellent 😊

Cyanic Acid	A-Excellent 😊
Cyclohexane	A-Excellent 😊
Cyclohexanone	A-Excellent 😊
Detergents	A-Excellent 😊
Diacetone Alcohol	A-Excellent 😊
Dichlorobenzene	A-Excellent 😊
Dichloroethane	A-Excellent 😊
Diesel Fuel	A-Excellent 😊
Diethyl Ether	A-Excellent 😊
Diethylamine	D-Severe Effect 😞
Diethylene Glycol	A-Excellent 😊
Dimethyl Aniline	A-Excellent 😊
Dimethyl Formamide	A-Excellent 😊
Diphenyl	A-Excellent 😊
Diphenyl Oxide	A-Excellent 😊
Dyes	N/A
Epsom Salts (Magnesium Sulfate)	A-Excellent 😊
Ethane	A-Excellent 😊
Ethanol	A-Excellent 😊
Ethanolamine	A-Excellent 😊
Ether	A-Excellent 😊
Ethyl Acetate	A-Excellent 😊
Ethyl Benzoate	A-Excellent 😊
Ethyl Chloride	A-Excellent 😊
Ethyl Ether	A-Excellent 😊
Ethyl Sulfate	A-Excellent 😊
Ethylene Bromide	A-Excellent 😊
Ethylene Chloride	A-Excellent 😊
Ethylene Chlorohydrin	A-Excellent 😊
Ethylene Diamine	A-Excellent 😊
Ethylene Dichloride	A-Excellent 😊
Ethylene Glycol	A-Excellent 😊
Ethylene Oxide	A-Excellent 😊
Fatty Acids	A-Excellent 😊
Ferric Chloride	A-Excellent 😊
Ferric Nitrate	A-Excellent 😊
Ferric Sulfate	A-Excellent 😊
Ferrous Chloride	A-Excellent 😊
Ferrous Sulfate	A-Excellent 😊

Fluoboric Acid	A-Excellent 😊
Fluorine	D-Severe Effect 😞
Fluosilicic Acid	A-Excellent 😊
Formaldehyde 100%	A-Excellent 😊
Formaldehyde 40%	A-Excellent 😊
Formic Acid	A-Excellent 😊
Freon 113	A-Excellent 😊
Freon 12	A-Excellent 😊
Freon 22	A-Excellent 😊
Freon TF	A-Excellent 😊
Freonr 11	A-Excellent 😊
Fruit Juice	A-Excellent 😊
Fuel Oils	B-Good 😊
Furan Resin	A-Excellent 😊
Furfural	A-Excellent 😊
Gallic Acid	B-Good 😊
Gasoline (high-aromatic)	B-Good 😊
Gasoline, leaded, ref.	A-Excellent 😊
Gasoline, unleaded	A-Excellent 😊
Gelatin	A-Excellent 😊
Glucose	A-Excellent 😊
Glue, P.V.A.	A-Excellent 😊
Glycerin	A-Excellent 😊
Glycolic Acid	A-Excellent 😊
Gold Monocyanide	D-Severe Effect 😞
Grape Juice	A-Excellent 😊
Grease	A-Excellent 😊
Heptane	A-Excellent 😊
Hexane	A-Excellent 😊
Honey	A-Excellent 😊
Hydraulic Oil (Petro)	A-Excellent 😊
Hydraulic Oil (Synthetic)	A-Excellent 😊
Hydrazine	A-Excellent 😊
Hydrobromic Acid 100%	A-Excellent 😊
Hydrobromic Acid 20%	N/A
Hydrochloric Acid 100%	A-Excellent 😊
Hydrochloric Acid 20%	A-Excellent 😊
Hydrochloric Acid 37%	A-Excellent 😊
Hydrochloric Acid, Dry Gas	A-Excellent 😊

Hydrocyanic Acid	A-Excellent 😊
Hydrocyanic Acid (Gas 10%)	A-Excellent 😊
Hydrofluoric Acid 100%	A-Excellent 😊
Hydrofluoric Acid 20%	A-Excellent 😊
Hydrofluoric Acid 50%	A-Excellent 😊
Hydrofluoric Acid 75%	A-Excellent 😊
Hydrofluosilicic Acid 100%	A-Excellent 😊
Hydrofluosilicic Acid 20%	A-Excellent 😊
Hydrogen Gas	A-Excellent 😊
Hydrogen Peroxide 10%	A-Excellent 😊
Hydrogen Peroxide 100%	A-Excellent 😊
Hydrogen Peroxide 30%	A-Excellent 😊
Hydrogen Peroxide 50%	A-Excellent 😊
Hydrogen Sulfide (aqua)	A-Excellent 😊
Hydrogen Sulfide (dry)	A-Excellent 😊
Hydroquinone	A-Excellent 😊
Hydroxyacetic Acid 70%	A-Excellent 😊
Ink	A-Excellent 😊
Iodine	A-Excellent 😊
Iodine (in alcohol)	N/A
Iodoform	C-Fair 😐
Isooctane	A-Excellent 😊
Isopropyl Acetate	A-Excellent 😊
Isopropyl Ether	A-Excellent 😊
Isotane	N/A
Jet Fuel (JP3, JP4, JP5)	A-Excellent 😊
Kerosene	A-Excellent 😊
Ketones	A-Excellent 😊
Lacquer Thinners	A-Excellent 😊
Lacquers	A-Excellent 😊
Lactic Acid	A-Excellent 😊
Lard	A-Excellent 😊
Latex	A-Excellent 😊
Lead Acetate	A-Excellent 😊
Lead Nitrate	A-Excellent 😊
Lead Sulfamate	B-Good 😊
Ligroin	A-Excellent 😊
Lime	A-Excellent 😊
Linoleic Acid	A-Excellent 😊
Lithium Chloride	A-Excellent 😊

Lithium Hydroxide	A-Excellent 😊
Lubricants	A-Excellent 😊
Lye: Ca(OH) ₂ Calcium Hydroxide	A-Excellent 😊
Lye: KOH Potassium Hydroxide	A-Excellent 😊
Lye: NaOH Sodium Hydroxide	A-Excellent 😊
Magnesium Bisulfate	A-Excellent 😊
Magnesium Carbonate	A-Excellent 😊
Magnesium Chloride	A-Excellent 😊
Magnesium Hydroxide	A-Excellent 😊
Magnesium Nitrate	A-Excellent 😊
Magnesium Oxide	A-Excellent 😊
Magnesium Sulfate (Epsom Salts)	A-Excellent 😊
Maleic Acid	A-Excellent 😊
Maleic Anhydride	A-Excellent 😊
Malic Acid	A-Excellent 😊
Manganese Sulfate	A-Excellent 😊
Mash	N/A
Mayonnaise	A-Excellent 😊
Melamine	A-Excellent 😊
Mercuric Chloride (dilute)	A-Excellent 😊
Mercuric Cyanide	B-Good 😊
Mercurous Nitrate	A-Excellent 😊
Mercury	A-Excellent 😊
Methane	A-Excellent 😊
Methanol (Methyl Alcohol)	A-Excellent 😊
Methyl Acetate	A-Excellent 😊
Methyl Acetone	A-Excellent 😊
Methyl Acrylate	N/A
Methyl Alcohol 10%	A-Excellent 😊
Methyl Bromide	A-Excellent 😊
Methyl Butyl Ketone	N/A
Methyl Cellosolve	A-Excellent 😊
Methyl Chloride	A-Excellent 😊
Methyl Dichloride	N/A
Methyl Ethyl Ketone	A-Excellent 😊
Methyl Ethyl Ketone Peroxide	N/A
Methyl Isobutyl Ketone	A-Excellent 😊
Methyl Isopropyl Ketone	A-Excellent 😊
Methyl Methacrylate	N/A
Methylamine	A-Excellent 😊

Methylene Chloride	A-Excellent 😊
Milk	A-Excellent 😊
Mineral Spirits	A-Excellent 😊
Molasses	A-Excellent 😊
Monochloroacetic acid	A-Excellent 😊
Monoethanolamine	A-Excellent 😊
Morpholine	A-Excellent 😊
Motor oil	A-Excellent 😊
Mustard	A-Excellent 😊
Naphtha	B-Good 😊
Naphthalene	A-Excellent 😊
Natural Gas	A-Excellent 😊
Nickel Chloride	A-Excellent 😊
Nickel Nitrate	A-Excellent 😊
Nickel Sulfate	A-Excellent 😊
Nitrating Acid (<15% HNO3)	A-Excellent 😊
Nitrating Acid (>15% H2SO4)	A-Excellent 😊
Nitrating Acid (S1% Acid)	A-Excellent 😊
Nitrating Acid (S15% H2SO4)	A-Excellent 😊
Nitric Acid (20%)	A-Excellent 😊
Nitric Acid (50%)	A-Excellent 😊
Nitric Acid (5-10%)	A-Excellent 😊
Nitric Acid (Concentrated)	A-Excellent 😊
Nitrobenzene	A-Excellent 😊
Nitrogen Fertilizer	A-Excellent 😊
Nitromethane	A-Excellent 😊
Nitrous Acid	A-Excellent 😊
Nitrous Oxide	A-Excellent 😊
Oils:Aniline	A-Excellent 😊
Oils:Anise	N/A
Oils:Bay	N/A
Oils:Bone	A-Excellent 😊
Oils:Castor	A-Excellent 😊
Oils:Cinnamon	A-Excellent 😊
Oils:Citric	A-Excellent 😊
Oils:Clove	A-Excellent 😊
Oils:Coconut	A-Excellent 😊
Oils:Cod Liver	A-Excellent 😊
Oils:Corn	A-Excellent 😊
Oils:Cottonseed	A-Excellent 😊

Oils:Creosote	A-Excellent 😊
Oils:Diesel Fuel (20, 30, 40, 50)	A-Excellent 😊
Oils:Fuel (1, 2, 3, 5A, 5B, 6)	A-Excellent 😊
Oils:Ginger	A-Excellent 😊
Oils:Hydraulic Oil (Petro)	A-Excellent 😊
Oils:Hydraulic Oil (Synthetic)	A-Excellent 😊
Oils:Lemon	A-Excellent 😊
Oils:Linseed	A-Excellent 😊
Oils:Mineral	A-Excellent 😊
Oils:Olive	A-Excellent 😊
Oils:Orange	N/A
Oils:Palm	A-Excellent 😊
Oils:Peanut	A-Excellent 😊
Oils:Peppermint	A-Excellent 😊
Oils:Pine	A-Excellent 😊
Oils:Rapeseed	A-Excellent 😊
Oils:Rosin	A-Excellent 😊
Oils:Sesame Seed	A-Excellent 😊
Oils:Silicone	A-Excellent 😊
Oils:Soybean	A-Excellent 😊
Oils:Sperm (whale)	A-Excellent 😊
Oils:Tanning	N/A
Oils:Transformer	A-Excellent 😊
Oils:Turbine	A-Excellent 😊
Oleic Acid	A-Excellent 😊
Oleum 100%	A-Excellent 😊
Oleum 25%	A-Excellent 😊
Oxalic Acid (cold)	A-Excellent 😊
Ozone	A-Excellent 😊
Palmitic Acid	A-Excellent 😊
Paraffin	A-Excellent 😊
Pentane	A-Excellent 😊
Perchloric Acid	A-Excellent 😊
Perchloroethylene	A-Excellent 😊
Petrolatum	C-Fair 😐
Petroleum	A-Excellent 😊
Phenol (10%)	A-Excellent 😊
Phenol (Carbolic Acid)	A-Excellent 😊
Phosphoric Acid (>40%)	A-Excellent 😊
Phosphoric Acid (crude)	A-Excellent 😊

Phosphoric Acid (molten)	N/A
Phosphoric Acid (S40%)	A-Excellent 😊
Phosphoric Acid Anhydride	N/A
Phosphorus	A-Excellent 😊
Phosphorus Trichloride	A-Excellent 😊
Photographic Developer	A-Excellent 😊
Photographic Solutions	A-Excellent 😊
Phthalic Acid	A-Excellent 😊
Phthalic Anhydride	A-Excellent 😊
Picric Acid	A-Excellent 😊
Plating Solutions, Antimony Plating 130°F	A-Excellent 😊
Plating Solutions, Arsenic Plating 110°F	A-Excellent 😊
Plating Solutions, Brass Plating: High-Speed Brass Bath 110°F	A-Excellent 😊
Plating Solutions, Brass Plating: Regular Brass Bath 100°F	A-Excellent 😊
Plating Solutions, Bronze Plating: Cu-Cd Bronze Bath R.T.	A-Excellent 😊
Plating Solutions, Bronze Plating: Cu-Sn Bronze Bath 160°F	A-Excellent 😊
Plating Solutions, Bronze Plating: Cu-Zn Bronze Bath 100°F	A-Excellent 😊
Plating Solutions, Cadmium Plating: Cyanide Bath 90°F	A-Excellent 😊
Plating Solutions, Cadmium Plating: Fluoborate Bath 100°F	A-Excellent 😊
Plating Solutions, Chromium Plating: Barrel Chrome Bath 95°F	A-Excellent 😊
Plating Solutions, Chromium Plating: Black Chrome Bath 115°F	A-Excellent 😊
Plating Solutions, Chromium Plating: Chromic-Sulfuric Bath 130°F	A-Excellent 😊
Plating Solutions, Chromium Plating: Fluoride Bath 130°F	A-Excellent 😊
Plating Solutions, Chromium Plating: Fluosilicate Bath 95°F	A-Excellent 😊
Plating Solutions, Copper Plating (Acid): Copper Fluoborate Bath 120°F	A-Excellent 😊
Plating Solutions, Copper Plating (Acid): Copper Sulfate Bath R.T.	A-Excellent 😊
Plating Solutions, Copper Plating (Cyanide): Copper Strike Bath 120°F	A-Excellent 😊
Plating Solutions, Copper Plating (Cyanide): High-Speed Bath 180°F	A-Excellent 😊
Plating Solutions, Copper Plating (Cyanide): Rochelle Salt Bath 150°F	A-Excellent 😊
Plating Solutions, Copper Plating (Misc): Copper (Electroless)	A-Excellent 😊
Plating Solutions, Copper Plating (Misc): Copper Pyrophosphate	A-Excellent 😊

Plating Solutions, Gold Plating: Acid 75°F	A-Excellent 😊
Plating Solutions, Gold Plating: Cyanide 150°F	A-Excellent 😊
Plating Solutions, Gold Plating: Neutral 75°F	A-Excellent 😊
Plating Solutions, Indium Sulfamate Plating R.T.	A-Excellent 😊
Plating Solutions, Iron Plating: Ferrous Am Sulfate Bath 150°F	A-Excellent 😊
Plating Solutions, Iron Plating: Ferrous Chloride Bath 190°F	A-Excellent 😊
Plating Solutions, Iron Plating: Ferrous Sulfate Bath 150°F	A-Excellent 😊
Plating Solutions, Iron Plating: Fluoborate Bath 145°F	A-Excellent 😊
Plating Solutions, Iron Plating: Sulfamate 140°F	A-Excellent 😊
Plating Solutions, Iron Plating: Sulfate-Chloride Bath 160°F	A-Excellent 😊
Plating Solutions, Lead Fluoborate Plating	A-Excellent 😊
Plating Solutions, Nickel Plating: Electroless 200°F	A-Excellent 😊
Plating Solutions, Nickel Plating: Fluoborate 100-170°F	A-Excellent 😊
Plating Solutions, Nickel Plating: High-Chloride 130-160°F	A-Excellent 😊
Plating Solutions, Nickel Plating: Sulfamate 100-140°F	A-Excellent 😊
Plating Solutions, Nickel Plating: Watts Type 115-160°F	A-Excellent 😊
Plating Solutions, Rhodium Plating 120°F	A-Excellent 😊
Plating Solutions, Silver Plating 80- 120°F	A-Excellent 😊
Plating Solutions, Tin-Fluoborate Plating 100°F	A-Excellent 😊
Plating Solutions, Tin-Lead Plating 100°F	A-Excellent 😊
Plating Solutions, Zinc Plating: Acid Chloride 140°F	A-Excellent 😊
Plating Solutions, Zinc Plating: Acid Fluoborate Bath R.T.	A-Excellent 😊
Plating Solutions, Zinc Plating: Acid Sulfate Bath 150°F	A-Excellent 😊
Plating Solutions, Zinc Plating: Alkaline Cyanide Bath R.T.	A-Excellent 😊
Potash (Potassium Carbonate)	N/A
Potassium Bicarbonate	A-Excellent 😊
Potassium Bromide	A-Excellent 😊
Potassium Chlorate	A-Excellent 😊
Potassium Chloride	A-Excellent 😊
Potassium Chromate	A-Excellent 😊

Potassium Cyanide Solutions	A-Excellent 😊
Potassium Dichromate	A-Excellent 😊
Potassium Ferricyanide	A-Excellent 😊
Potassium Ferrocyanide	A-Excellent 😊
Potassium Hydroxide (Caustic Potash)	A-Excellent 😊
Potassium Hypochlorite	A-Excellent 😊
Potassium Iodide	A-Excellent 😊
Potassium Nitrate	A-Excellent 😊
Potassium Oxalate	A-Excellent 😊
Potassium Permanganate	A-Excellent 😊
Potassium Sulfate	A-Excellent 😊
Potassium Sulfide	A-Excellent 😊
Propane (liquefied)	A-Excellent 😊
Propylene	A-Excellent 😊
Propylene Glycol	A-Excellent 😊
Pyridine	A-Excellent 😊
Pyrogallic Acid	A-Excellent 😊
Resorcinal	A-Excellent 😊
Rosins	A-Excellent 😊
Rum	N/A
Rust Inhibitors	N/A
Salad Dressings	N/A
Salicylic Acid	A-Excellent 😊
Salt Brine (NaCl saturated)	A-Excellent 😊
Sea Water	A-Excellent 😊
Shellac (Bleached)	A-Excellent 😊
Shellac (Orange)	A-Excellent 😊
Silicone	A-Excellent 😊
Silver Bromide	A-Excellent 😊
Silver Nitrate	A-Excellent 😊
Soap Solutions	A-Excellent 😊
Soda Ash (see Sodium Carbonate)	A-Excellent 😊
Sodium Acetate	A-Excellent 😊
Sodium Aluminate	A-Excellent 😊
Sodium Benzoate	A-Excellent 😊
Sodium Bicarbonate	A-Excellent 😊
Sodium Bisulfate	A-Excellent 😊
Sodium Bisulfite	A-Excellent 😊
Sodium Borate (Borax)	A-Excellent 😊

Sodium Bromide	A-Excellent 😊
Sodium Carbonate	A-Excellent 😊
Sodium Chlorate	A-Excellent 😊
Sodium Chloride	A-Excellent 😊
Sodium Chromate	A-Excellent 😊
Sodium Cyanide	A-Excellent 😊
Sodium Ferrocyanide	A-Excellent 😊
Sodium Fluoride	A-Excellent 😊
Sodium Hydrosulfite	A-Excellent 😊
Sodium Hydroxide (20%)	A-Excellent 😊
Sodium Hydroxide (50%)	A-Excellent 😊
Sodium Hydroxide (80%)	A-Excellent 😊
Sodium Hypochlorite (<20%)	A-Excellent 😊
Sodium Hypochlorite (100%)	A-Excellent 😊
Sodium Hyposulfate	A-Excellent 😊
Sodium Metaphosphate	A-Excellent 😊
Sodium Metasilicate	A-Excellent 😊
Sodium Nitrate	A-Excellent 😊
Sodium Perborate	A-Excellent 😊
Sodium Peroxide	A-Excellent 😊
Sodium Polyphosphate	A-Excellent 😊
Sodium Silicate	A-Excellent 😊
Sodium Sulfate	A-Excellent 😊
Sodium Sulfide	A-Excellent 😊
Sodium Sulfite	A-Excellent 😊
Sodium Tetraborate	A-Excellent 😊
Sodium Thiosulfate (hypo)	A-Excellent 😊
Sorghum	N/A
Soy Sauce	N/A
Stannic Chloride	A-Excellent 😊
Stannic Fluoborate	N/A
Stannous Chloride	A-Excellent 😊
Starch	A-Excellent 😊
Stearic Acid	A-Excellent 😊
Stoddard Solvent	A-Excellent 😊
Styrene	A-Excellent 😊
Sugar (Liquids)	A-Excellent 😊
Sulfate (Liquors)	A-Excellent 😊
Sulfur Chloride	A-Excellent 😊
Sulfur Dioxide	A-Excellent 😊

Sulfur Dioxide (dry)	A-Excellent 😊
Sulfur Hexafluoride	N/A
Sulfur Trioxide	A-Excellent 😊
Sulfur Trioxide (dry)	A-Excellent 😊
Sulfuric Acid (<10%)	A-Excellent 😊
Sulfuric Acid (10-75%)	A-Excellent 😊
Sulfuric Acid (75-100%)	A-Excellent 😊
Sulfuric Acid (cold concentrated)	A-Excellent 😊
Sulfuric Acid (hot concentrated)	A-Excellent 😊
Sulfurous Acid	A-Excellent 😊
Sulfuryl Chloride	A-Excellent 😊
Tallow	A-Excellent 😊
Tannic Acid	A-Excellent 😊
Tanning Liquors	A-Excellent 😊
Tartaric Acid	A-Excellent 😊
Tetrachloroethane	A-Excellent 😊
Tetrachloroethylene	A-Excellent 😊
Tetrahydrofuran	A-Excellent 😊
Tin Salts	A-Excellent 😊
Toluene (Toluol)	A-Excellent 😊
Tomato Juice	A-Excellent 😊
Trichloroacetic Acid	A-Excellent 😊
Trichloroethane	A-Excellent 😊
Trichloroethylene	A-Excellent 😊
Trichloropropane	A-Excellent 😊
Tricresylphosphate	A-Excellent 😊
Triethylamine	A-Excellent 😊
Trisodium Phosphate	A-Excellent 😊
Turpentine	A-Excellent 😊
Urea	A-Excellent 😊
Uric Acid	A-Excellent 😊
Urine	A-Excellent 😊
Varnish	A-Excellent 😊
Vegetable Juice	A-Excellent 😊
Vinegar	A-Excellent 😊
Vinyl Acetate	A-Excellent 😊
Vinyl Chloride	A-Excellent 😊
Water, Acid, Mine	A-Excellent 😊
Water, Deionized	A-Excellent 😊

Water, Distilled	A-Excellent 😊
Water, Fresh	A-Excellent 😊
Water, Salt	A-Excellent 😊
Weed Killers	N/A
Whey	A-Excellent 😊
Whiskey & Wines	A-Excellent 😊
White Liquor (Pulp Mill)	A-Excellent 😊
White Water (Paper Mill)	N/A
Xylene	A-Excellent 😊
Zinc Chloride	A-Excellent 😊
Zinc Hydrosulfite	A-Excellent 😊
Zinc Sulfate	A-Excellent 😊